

トクシール代表物性

製品	比表面積	pH(5%)	水分	強熱減量	見掛比重	かさ比重	吸油量	シリカ分	平均粒子径
	m ² /g		%	%	g/ml	g/ml	ml/100g	%	μm
Tokusil U	175.0	6.5	6.2	10.4	0.21		230.0	98.1	13.2
Tokusil UR	178.0	6.5	6.4	9.8	0.26		220.0	98.2	
Tokusil GU-N		6.7	6.5	9.7	0.21		230.0	98.1	17.8
Tokusil NR	191.0	6.2	5.8	10.2		0.14	280.0	98.3	
Tokusil PR	201.0		5.7	9.3		0.19	250.0	98.5	
Tokusil USA	197.0	6.2	5.5	8.9		0.09	200.0	99.1	14.2
Tokusil GU	121.0	8.0	8.1	11.5	0.24		160.0	92.3	15.5
Tokusil NP	190.0	6.1	6.2	10.2		0.063	240.0	98.0	10.3
Tokusil NPS	190.0	5.0	6.1	10.4		0.063	250.0	98.0	9.8
Tokusil 315	190.0	6.9	5.9	11.8	0.31		n/a	>93	
Tokusil 233	149.0	6.9	5.8	10.9	0.26		220.0	>93	120.0
Tokusil 255	169.0	6.6	6.2	9.7	0.27		220.0	>93	120.0
Tokusil 255LD	174.0	6.5	6.3	10.2	0.27		230.0	>93	250.0
Tokusil 233G	151.0	6.8	5.8	11.1	0.3		n/a	>93	
Tokusil 255G	176.0	6.5	6.3	9.8	0.31		210.0	>93	
Tokusil 195G	193.0	6.5	5.5	10.2	0.2		220.0	>93	13.2
Tokusil 200G	148.0	5.7	6.2	10.3	0.3		210.0	>93	
Tokusil USG-T	210.0	6.1	6.0	9.9	0.31		n/a	>93	
Tokusil 315EG	111.0	6.5	5.8	8.9	0.31		210.0	>93	
Tokusil 255EG	172.0	6.1	5.7	11.3	0.31		n/a	>93	
Tokusil 923	201.0	6.8	5.5	10.3	0.18		260.0	>94	11.1
Tokusil 928	195.0	6.6	5.4	10.2	0.17		220.0	>94	11.8
Tokusil 532	91.0	8.6	6.9		0.17		190.0	>93	15.8
Tokusil 732	61.0	9.7	6.8		0.25		170.0	>93	15.9
分析方法	ISO 5794-1	ISO 787-9	ISO 787-2	ISO 3262-19	JIS K6220-1	JIS K5101-12-1	JIS 4656	ISO 5794-1	粒度分布計